

TEST REPORT

No. : SC081220891

Date : Feb.19,2009

Page: 1 of 7

LIYNIX ENTERPRISE CO.,LTD

3F, BUILDING 3, NO.1221 YAN AN XI RD SHANGHAI

The following sample(s) was/ were submitted and identified on behalf of the client as:

Sample Name : TANCHOR
 Sample No : SC081220891
 Test Required : Please see next pages
 Test Method : Please see next pages
 Product specification : HBC40/25 300MM
 Manufacturer : LIYNIX ENTERPRISE CO.,LTD
 Date of Receipt : Dec.23,2008
 Test Period : Dec.23,2008 to Feb.19,2009
 Test results : Please see next pages

*****To be continued *****

Signed for SGS-CSTC Standards
 Technical Services Co., Ltd

Joanna

Joanna Wang
 Lab Technical Supervisor

This document is issued by the Company under its General Conditions of Service printed overleaf or available on request and accessible at <http://www.sgs.com/terms.and.conditions.htm>. Attention is drawn to the limitation of liability, indemnification and jurisdiction issues defined therein. Any holder of this document is advised that information contained hereon reflects the findings at the time of its intervention only and within the limits of Client's instructions, if any. The Company's sole responsibility is to its Client and this document does not exonerate parties to a transaction from exercising all their rights and obligations under the transaction documents. Any unauthorized alteration, forgery or falsification of the content or appearance of this document is unlawful and offenders may be prosecuted to the fullest extent of the law. Unless otherwise stated the results shown in this test report refer only to the sample(s) tested and such sample(s) are retained for 30 days only. This document cannot be reproduced except in full without prior approval of the Company.

TEST REPORT

No. : SC081220891

Date : Feb.19,2009

Page: 2 of 7

Tensile Loading Test of TANCHOR Cold Formed Channel

1. Brief Introduction

LIYNIX ENTERPRISE Co., Ltd.(3F, Building 3, No.1221, Yan an xi Rd, Shanghai, P.R.C)consigns SGS-CSTC Standard Technical Services Co., Ltd. to test the tensile loading test of TANCHOR Cold Formed Channel. The type of the sample is HBC40/25 300MM, provided by consigner. The concrete is molded and built in by SGS.

The molding concrete is commercial concrete transported by pump which strength grade is C35. The curing age is 28 days.

2. Test Method

Refer to BS 5080-1:1993 Structural fixings in concrete and masonry ---Part 1: Method of test for tensile loading

3. Test Equipments

No.	Equipment	Type
1	ENERPAC Bolt pull test apparatus	P80
2	Dial indicator	0~10mm
3	Digital Gauge for Force	Z50

4. Test Results

4.1 Description of Concrete

Design Strength	Molding Date	Test Date	Provider of Concrete	Concrete Strength Grade
C35	2009-01-14	2009-02-13	Shanghai Shuangqiu commercial concrete Co., Ltd.	C35

*****To be continued *****

This document is issued by the Company under its General Conditions of Service printed overleaf or available on request and accessible at http://www.sgs.com/terms_and_conditions.htm. Attention is drawn to the limitation of liability, indemnification and jurisdiction issues defined therein. Any holder of this document is advised that information contained hereon reflects the findings at the time of its intervention only and within the limits of Client's instructions, if any. The Company's sole responsibility is to its Client and this document does not constitute a transaction from exercising all their rights and obligations under the transaction documents. Any unauthorized alteration, forgery or falsification of the content or appearance of this document is unlawful and offenders may be prosecuted to the fullest extent of the law. Unless otherwise stated, the results shown in this test report refer only to the sample(s) tested and such sample(s) are retained for 30 days only. This document cannot be reproduced except in full without prior approval of the Company.

TEST REPORT

No. : SC081220891

Date : Feb.19,2009

Page: 3 of 7

4.2 Test Results of TANCHOR Cold Formed Channel

No.	Sample Type	Design Load (kN)	Break Load (kN)	Test Result			
				Maximum Load (kN)	Average of Maximum Effective Deflection (mm)	Breaking Form of Samples	Conclusion
1	HBC40/2 5 300MM	16	48	62.7	2.31	The channel part of the sample was split.	Meet the design requirement.
2				60.1	3.88	The channel part of the sample was split.	Meet the design requirement.
3				61.5	2.72	The channel part of the sample was split.	Meet the design requirement.

Annex 1: Test results of each sample

Annex 2: Samples Drawing

Annex 3: Test Photo

Annex 1: Test results of each sample

Table 1 Test results of Sample 1

No.	Load (kN)	Deflection (mm)		Average Deflection (mm)
		1	2	
1	5	0.07	0.06	0.06
2	10	0.13	0.14	0.14
3	15	0.23	0.23	0.23
4	20	0.38	0.34	0.36
5	25	0.60	0.45	0.52
6	30	0.90	0.61	0.76
7	35	1.32	0.89	1.10
8	40	1.78	1.31	1.54
9	45	2.51	2.11	2.31

*****To be continued *****

This document is issued by the Company under its General Conditions of Service printed overleaf or available on request and accessible at <http://www.sgs.com/termsandconditions.htm>. Attention is drawn to the limitation of liability, indemnification and jurisdiction issues defined therein. Any holder of this document is advised that information contained hereon reflects the findings at the time of its intervention only and within the limits of Client's instructions, if any. The Company's sole responsibility is to its Client and this document does not constitute any part of a transaction from exercising all their rights and obligations under the transaction documents. Any unauthorized alteration, forgery or falsification of the content or appearance of this document is unlawful and offenders may be prosecuted to the fullest extent of the law. Unless otherwise stated the results shown in this test report refer only to the sample(s) tested and such sample(s) are retained for 30 days only. This document cannot be reproduced except in full without prior approval of the Company.

TEST REPORT

No. : SC081220891

Date : Feb.19,2009

Page: 4 of 7




Fig.1 Average Deflection-Load graph of Sample1

Table 2 Test results of Sample 2

No.	Load (kN)	Deflection (mm)		Average Deflection (mm)
		1	2	
1	5	0.00	0.00	0.00
2	10	0.15	0.19	0.17
3	15	0.25	0.21	0.23
4	20	0.56	0.71	0.64
5	25	0.93	1.07	1.00
6	30	1.45	1.44	1.44
7	35	2.10	2.20	2.15
8	40	2.66	2.75	2.70
9	45	3.86	3.90	3.88

*****To be continued *****

This document is issued by the Company under its General Conditions of Service printed overleaf or available on request and accessible at <http://www.sgs.com/termsandconditions.htm>. Attention is drawn to the limitation of liability, indemnification and jurisdiction issues defined therein. Any holder of this document is advised that information contained hereon reflects the findings at the time of its intervention only and within the limits of Client's instructions, if any. The Company's sole responsibility is to its Client and this document does not constitute a transaction from exercising all their rights and obligations under the transaction documents. Any unauthorized alteration, forgery or falsification of the content or appearance of this document is unlawful and offenders may be prosecuted to the fullest extent of the law. Unless otherwise stated the results shown in this test report refer only to the sample(s) tested and such sample(s) are retained for 30 days only. This document cannot be reproduced except in full without prior approval of the Company.



TEST REPORT

No. : SC081220891

Date : Feb.19,2009

Page: 5 of 7




Fig.2 Average Deflection-Load graph of Sample2

Table 3 Test results of Sample 3

No.	Load (kN)	Deflection (mm)		Average Deflection (mm)
		1	2	
1	5	0.01	0.02	0.02
2	10	0.02	0.11	0.06
3	15	0.14	0.18	0.16
4	20	0.39	0.36	0.38
5	25	0.61	0.40	0.50
6	30	1.17	0.59	0.88
7	35	2.17	0.72	1.44
8	40	2.84	1.02	1.93
9	45	3.69	1.74	2.72

*****To be continued *****

This document is issued by the Company under its General Conditions of Service printed overleaf or available on request and accessible at <http://www.sgs.com/termsandconditions.htm>. Attention is drawn to the limitation of liability, indemnification and jurisdiction issues defined therein. Any holder of this document is advised that information contained hereon reflects the findings at the time of its intervention only and within the limits of Client's instructions, if any. The Company's sole responsibility is to its Client and this document does not constitute a transaction from exercising all their rights and obligations under the transaction documents. Any unauthorized alteration, forgery or falsification of the content or appearance of this document is unlawful and offenders may be prosecuted to the fullest extent of the law. Unless otherwise stated the results shown in this test report refer only to the sample(s) tested and such sample(s) are retained for 30 days only. This document cannot be reproduced except in full without prior approval of the Company.

TEST REPORT

No. : SC081220891

Date : Feb.19,2009

Page: 6 of 7





Fig.3 Average Deflection-Load graph of Sample3

Annex 2: Samples Drawing



*****To be continued *****

This document is issued by the Company under its General Conditions of Service printed overleaf or available on request and accessible at <http://www.sgs.com/terms.and.conditions.htm>. Attention is drawn to the limitation of liability, indemnification and jurisdiction issues defined therein. Any holder of this document is advised that information contained hereon reflects the technical findings at the time of its intervention only and within the limits of Client's instructions, if any. The Company's sole responsibility is to its Client and this document does not constitute a contract. The Company does not warrant the accuracy or appearance of this document is unlawful and offenders may be prosecuted to the fullest extent of the law. Unless otherwise stated the results shown in this test report refer only to the sample(s) tested and such sample(s) are retained for 30 days only. This document cannot be reproduced except in full without prior approval of the Company.


TEST REPORT

No. : SC081220891

Date : Feb.19,2009

Page: 7 of 7

Annex 3: Test Photos:



*****End of report*****

This document is issued by the Company under its General Conditions of Service printed overleaf or available on request and accessible at <http://www.sgs.com/terms.and.conditions.htm>. Attention is drawn to the limitation of liability, indemnification and jurisdiction issues defined therein. Any holder of this document is advised that information contained hereon reflects the findings at the time of its intervention only and within the limits of Client's instructions, if any. The Company's sole responsibility is to its Client and this document does not exonerate parties to a transaction from exercising all their rights and obligations under the transaction documents. Any unauthorized alteration, forgery or falsification of the content or appearance of this document is unlawful and offenders may be prosecuted to the fullest extent of the law. Unless otherwise stated the results shown in this test report refer only to the sample(s) tested and such sample(s) are retained for 30 days only. This document cannot be reproduced except in full without prior approval of the Company.



8th Building, No.89 Block 1159/117th Building, Block 1365, Kangqiao East Road, Pudong Dist., Shanghai, China 201319 t (86-21) 68183233 / 68183239 f (86-21) 68183122 / 68183906 www.cn.sgs.com
中国·上海·浦东康桥东路1365弄17号楼/1159弄69号8号楼 邮编 201319 t (86-21) 68183233 / 68183239 f (86-21) 68183122 / 68183906 e sgs.china@sgs.com

SHML 130600

Member of the SGS Group (SGS SA)